

Technical Data

Garomat CSM-600E

Characteristics

CSM-600E is the chopped strand mat that is specially designed for hand lay-up contact moulding and it has excellent performance in the following areas:

- Good wet-out in resin
- UP resin compatible
- Good tensile strength with flexibility
- Highly soluble resin binder
- Excellent fibre distribution
- Uniform weight
- Excellent translucency

Specification

Test Item	Standard	Unit
Area Weight	600 ± 10	G/m²
Binder Content	3.0 - 4.5	%
Water Content	<0.3	%
Tensile Strength MD	≥70	N/150mm
Tensile Strength CD	≥70	N/150mm

Packing and Storage

Each roll is packed in a plastic bag and is wrapped up in a sleeve. E-CSM-600E should be stored in closed containers at a temperature between -10°C and 40°C for no more than 12 months and protected from frost and direct sunlight

The information contained in the Technical Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Omya believes to be reliable, however Omya makes no representation or warranty as to the completeness of accuracy thereof and Omya assumes no liability resulting from its use or for claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the materials suitability (including safety) for a particular purpose prior to such use.

Omya UK Ltd | Melton Office | Melton Bottom | Melton, North Ferriby| East Yorkshire | HU14 3HU Phone: +44 (0)1482 636 900 | Fax: +44 (0)1482 636 880 | www.omya.co.uk